

# Bio-sensitized Solar Cells

Ane Galarneau\*

Research Director, CNRS Institute Charles Gerhardt of Montpellier, France

## Introduction

With the world's population growing at an alarming rate, the need for energy will be the most pressing issue for the next 50 years. The majority of energy is now generated by the combustion of fossil fuels, however the widespread use of fossil fuels increases the concentration of CO<sub>2</sub> in the atmosphere, which causes global warming. A search for a free, clean, and sustainable energy source as a result, carbon has emerged as a critical concern for scientists. The most apparent source is the sun, which provides around ten thousand times the energy required by all of humanity. Presently we consume solar photovoltaic cells, which are capable of direct conversion of sunlight into electrical power. Top possibilities for a future clean and renewable source of vitality [1].

## About the Study

Although Si-based solar cells have been developed and commercialised for more than 30 years, a dye-sensitized solar cell is the most promising photovoltaic cell. The concept for this DSSC was first proposed in the early 1970s, but Grätzel and his colleagues made significant progress in 1991. A photo-active dye, a mesoporous nanocrystalline semiconductor layer coated on a transparent conducting oxide substrate, a liquid electrolyte, and a Pt-coated TCO substrate are typical components of a DSSC device [2]. When excited, the dye molecules inject electrons into the nanocrystalline semiconductor's conduction band. The TCO anode collects electrons, which travel via the outside circuit to the Pt-coated cathode. The surplus electrons at the cathode decrease it to three, and the three are oxidised back to regenerate the dye molecules at the anode.

Molecules of an appropriately chosen dye play an important role in determining overall cell performance in a DSSC; many dyes, including ruthenium polypyridine complexes, phthalocyanine, xanthenes, and coumarins, have thus been tested as potential sensitizers. The highest power conversion efficiency, 11%, was reached utilising ruthenium bi-pyridine derivatives, although the poisonous and rare synthetic organic and inorganic dyes present issues in their mass manufacture and environmental effect. For these reasons, the search for natural dye compounds has been a major focus of research [3].

Current cutting-edge dye sensitised solar cell platforms can attain sunlight harvesting efficiencies of more than 12%, which is equivalent to polycrystalline silicon solar cells. The majority of current research is to improve DSSC efficiency for commercial applications requiring brittle indium tin oxide glass substrates and temperature sensitive dyes and electrolytes. Platforms based on flexible ITO/polyethylene terephthalate electrodes have been developed to increase applicability, but no emphasis has been placed on developing

very flexible DSSC electrodes for extreme environmental and mechanical stress. The cutting-edge liquid iodine electrolyte and ruthenium dyes operate admirably in stable conditions, but they fail fast in severe temperatures and physical damage to external electrodes [4].

With increasing temperature, the conduction band of the liquid iodine electrolyte bends towards the valence band, causing a rise in exciton recombination, a drop in cell voltage output, and finally denaturing of the ruthenium dye. Temperature variations cause fast volume changes in liquid electrolytes, causing cell destruction, while rips or tears in the electrodes cause rapid evaporation of the liquid electrolyte, resulting in cell inoperability. TiO<sub>2</sub> nanotubes have a highly organised structure with vertical pore geometry, making them ideal for the fabrication of liquid-state junction cells. This is largely because nanotubes have a one-dimensional conductive channel as opposed to the three-dimensional unsystematic walk network and grain boundary effects associated with randomly ordered nanoparticles. It has been demonstrated that aligned TiO<sub>2</sub> nanotube arrays outperform typical TiO<sub>2</sub> nanoparticle films of the same thickness in terms of light scattering and collecting efficiency.

In addition to the electron collecting substrate, the use of strong dye pigments is emphasised. Specific biomaterials, such as optical membrane proteins, can provide improved thermal or chemical resistance, longevity, and possibly higher sun harvesting efficiency than existing state-of-the-art ruthenium dyes. Specifically, the retinal protein bacteriorhodopsin has a maximum theoretical light-harvesting efficiency of 25% and an average specific power of, 103 W/kg, but silicon has only 18% and 32 W/kg, respectively. Recent research has also shown that incorporating colloidal semiconductor quantum dots into bR can boost photon uptake by 20-fold and bR output by 300%, making bR an excellent biomolecule for sensitised solar cell systems.

Anthocyanins, for example, have recently shown promise as a low-cost and viable alternative to traditional synthetic dyes. Anthocyanin, which belongs to the flavonoid class, is found in the tissues of many different fruits and plants. Anthocyanins absorb light in the blue-green area between 450 and 600 nm wavelengths in cell vacuoles, allowing many fruits and plants to reflect red, purple, or blue. The anthocyanin absorption spectrum can be modified according to the kind of anthocyanin, pH, the sugar attached, and where the sugar is situated on the anthocyanin molecule structure.

This research aims to improve the DSSC platform's robustness by incorporating advanced biological dyes, a stable gel-polymer electrolyte, and an enhanced electron conduction pathway using TiO<sub>2</sub>. Highly ordered TiO<sub>2</sub> NTs were synthesised in an electrolyte solution using a dual anodization method on Ti. Anodization duration, voltage, and electrolyte composition were used to adjust the length, diameter, and wall thickness of the nanotubes. Nitrogen drying was used to remove NT sheets, which were then annealed at 450°C.

Annual energy demands are growing dramatically over the world, and present technologies based on carbon fuel burning have resulted in considerable rises in atmospheric CO<sub>2</sub> levels. Renewable energy harvesting from the environment, such as solar energy conversion using photovoltaic devices, is an appealing option that tries to capture a fraction of the almost 175,000 terajoules of sun photonic energy that strikes the Earth each year. Current PV systems on the market are made of inorganic materials such as hazardous heavy metals and rare-earth elements, and have prohibitively expensive production procedures, expenses, and post-installation mobility. Furthermore, because of the specialised recycling needs, existing first-generation PVs are expected to create almost 80 million metric tonnes of garbage by 2050.

As a result, it is evident that additional advancement of present PV

\*Address for Correspondence: Ane Galarneau, Research Director, CNRS Institute Charles Gerhardt of Montpellier, France, E-mail: anegalarneau@gmail.com

Copyright: © 2022 Galarneau A. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

Date of Submission: 18 June, 2022, Manuscript No. jbsbe-22-73323; Editor Assigned: 21 June, 2022, PreQC No. P-73323; Reviewed: 25 June, 2022; QC No. Q-73323; Revised: 04 July, 2022; Manuscript No. R-73323; Published: 06 July, 2022, DOI: 10.37421/2155-6210.2022.13.342

technology is required to meet future energy demands. Bio-sensitized solar cells are a viable solution to overcome these challenges by utilising simple manufacturing procedures with non-toxic and plentiful materials. BSSCs are based on dye-sensitized solar cells, who pioneered the design of a photosensitizing dye incorporated into a thin-layer style device with much more relaxed manufacturing requirements and the ability to incorporate many different types of materials in device fabrication.

---

## Conclusion

Over the last several years, the creation and development of devices combining the major components of natural biological photosynthesis, primarily the solar-to-electrical energy conversion protein-pigment complexes, has emerged as an exciting topic of research. This field, which has emerged as an intriguing topic of investigation in recent years. These bio-sensitized devices

have the potential to be utilised in future applications such as photo-switchable biosensors, solar-to-chemical, and solar-to-electrical energy converting systems, laying the groundwork for a green energy economy.

---

## References

1. Zhang, Diming and Qingjun Liu. "Biosensors and bioelectronics on smartphone for portable biochemical detection." *Biosens Bioelectron* 75 (2016): 273-284.
2. Su, Kaiqi, Xianxin Qiu, Jiaru Fang, and Quchao Zou, et al. "An improved efficient biochemical detection method to marine toxins with a smartphone-based portable system-Bionic e-Eye." *Sens Actuators B Chem* 238 (2017): 1165-1172.
3. Li, Shuang, Daizong Ji, Gang Xu, and Jinglong Liu, et al. "Biosensors and Bioelectronics on Smartphone." *Handbook of Cell Biosens* (2022): 627-655.
4. Lu, Yanli, Zhenghan Shi and Qingjun Liu. "Smartphone-based biosensors for portable food evaluation." *Curr Opin Food Sci* 28 (2019): 74-81.

**How to cite this article:** Galarneau, Ane. "Bio-sensitized Solar Cells ." *J Biosens Bioelectron* 13 (2022): 342.